



Docket No.: M4065.0239/P239
(PATENT)

2812
#8/A
Bell
52402

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:
Larry Hillyer, et al.

Application No.: 09/653,561

Group Art Unit: 2812

Filed: August 31, 2000

Examiner: Ha T. Nguyen

For: METHOD AND MATERIAL FOR
REMOVING ETCH RESIDUE FROM
HIGH ASPECT RATIO CONTACT
SURFACES

RECEIVED
MAY 22 2002
TECHNOLOGY CENTER 2800

AMENDMENT

Box Non-Fee Amendment
Commissioner for Patents
Washington, DC 20231

Dear Sir:

In response to the Office Action dated January 17, 2002 (Paper No. 5),
rejecting claims 1-44 and 50-53, please amend the above-identified U.S. Patent application
as follows. A request for extension of time and appropriate fee are submitted herewith to
ensure timeliness of the amendment.

In the Specification:

At page 14, second full paragraph (line 10 to line 20), please replace with
the following.

A1
Titanium deposition in the contact opening 20 can be done in a manner known
in the art. For example, titanium is deposited on the wafer using a sputter process
commonly used with metals. A target containing titanium is surrounded by an argon
plasma. Ions from the plasma hit the target surface. The titanium atoms which are